

Specification

Bentonite

Paint - Grade Formula

Analysis	Result
Moisture Content @ (105°C ± 3°C)	11.0 %
Dry Screen Analysis Pass 100 US Mesh	99.8 %
pH (5 % suspension)	9.5
Wet Screen Analysis	
Residue bei 200 US Mesh	0.25
Swelling 2 gm/100mt	28
Monto morolinite	75

General Industrial Applications:

Removal of oil und juice-stains, deep petroleum drilling, filtering water that comes out of wells, manufacture of some medicines