

## Specification

### Gypsum

Constituents	%
Combined water	19.88
Loss of ignition	19.35
CaO	31.05
SO <sub>4</sub>	55.45
MgO	0.09
SiO	0.24
Fe <sub>2</sub> O <sub>3</sub>	0.76
Al <sub>2</sub> O <sub>3</sub>	0.08
Cl	0.02
CaSO <sub>4</sub> 2H <sub>2</sub> O (Purity)	94.98

It is the highest specification of Gypsum in Egypt and world-wide.

Weight of bag 30.3 kg that indicates 33 bags per ton.